



**Tyvek Moisture Barrier Bag  
1004 Series**

<b>Physical Properties</b>			
Structure	Tyvek – 170 Microns ± 60 Microns LDPE – 25 Microns Al Foil – 7 Microns LDPE – 25 Microns LLDPE – 80 Microns A/S Coating		
Thickness	307 Microns ± 60 Microns		
Puncture Strength	2.61	Kgf	JAS 1019
Sealing	3.17	Kgf/15mm	KS A 1512-96
Elongation	Width	41.2%	KS M 3001-91
	Length	30.7%	
Permeability	0.00047	g/sqin/24hr	KS A 1013-91
Surface Resistivity	Inner	10 <sup>-11</sup> Ohm / sq	LCD Megaohmeter Item A 50070
	Outer	10 <sup>-11</sup> Ohm / sq	
Tensile Strength	Width	445g/m <sup>2</sup>	KSM 3001-91
	Length	357g/m <sup>2</sup>	

05 November 2018 (ME02)