

## Product Data

Sheet, Conductive  
Corrugated

Code : 1103 Series

### Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18  
Toa Payoh Industrial Estate  
Singapore 318992

Tel : +65 63541511  
Fax : +65 63541711  
Email : sales@pro-pack.com.sg  
Website : www.pro-pack.com.sg

Regional Offices :

**Malaysia**  
Bold Pack Industries Sdn Bhd

**Indonesia**  
PT Pro-Pack Industries

**Thailand**  
Bold-Pack Materials (Thai) Co. Ltd

**Philippines**  
Pro-Pack Materials (Philippines) Inc.

**India**  
Pro-Pack Materials India Pvt Ltd

**China**  
Pro-Pack Materials (Wuxi) Co., Ltd

### Physical Properties

Wall Thickness	-	4	mm
Substance	-	700	Gm / M <sup>2</sup>
Tensile Strength	MD	23	Kg / Cm
Tensile Strength	TD	14	Kg / Cm
Elongation	MD	18	%
Elongation	TD	12	%
Dupont/Impact Strength	MD	20	Kg-Cm
Dupont/Impact Strength	TD	15	Kg-Cm
Bending Strength	MD	1.7	Kg / Cm
Bending Strength	TD	1.5	Kg / Cm
End Crush	MD	11.5	Kg / Cm
End Crush	TD	1.5	Kg / Cm
Flat Crush	-	6	Kg / Cm <sup>2</sup>
Surface Resistivity	-	< 10 <sup>5</sup>	Ohm / Sq