

Product Data

Sheet, Conductive PE
Foam

Model : AE-150

Code : 1105 Series



Physical Properties

Density	0.066	g / cm ³
Tensile Strength	0.82, 8.4	Mpa, kgf / cm ²
Elongation	80	%
Breaking Power	34, 3.5	N/cm, kgf / cm ²
Compressed Hardness	0.098, 1	Mpa, kgf / cm ²
25% Permanent Compressed %	2.4	%
Degree of Temperature Change (70 °C x 22 Hr)	-0.6	%
Absorbability (B Method)	0.001	g / cm ³
Surface Resistance	Less than 2.7 x 10 ⁵	Ohm / sq

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia
Bold Pack Industries Sdn Bhd

Indonesia
PT Pro-Pack Industries

Thailand
Bold-Pack Materials (Thai) Co. Ltd

Philippines
Pro-Pack Materials (Philippines) Inc.

India
Pro-Pack Materials India Pvt Ltd

China
Pro-Pack Materials (Wuxi) Co., Ltd