



**Pink Antistatic LDPE Bag
1302 Series**

Feature	Benefit
Permanent antistatic	ESD protection
Transparent	Identified product been pack
Non corrosive	Will not affect metal part

Physical Properties

Tear Strength	1200	g	ASTM D922
Tensile Strength	185	Kg/sq.cm	ASTM D822
Water Absorption (24 Hr)	0.01	%	-
Heating Temperature	82 - 121	°C	-
Sealing Time	0.5 - 5	Sec	-
Maximum Temperature	93	°C	-
Minimum Temperature	15	°C	-

Electrical Properties

Static Decay Test (from 5KV to 1% at 73°F to 15% RH)	< 2	Sec	Method 4046
Surface Resistance	< 10 ¹⁰ – 10 ¹¹	Ohm	ANSI ESD STM 11.11

05 November 2018 (AS01)