

## Product Data

Sheet, Antistatic PE Foam

Code : 1403 Series



### Electrical Properties

Static Decay Test (From 5000V to 1% at 73°F, 12% RH)	< 2	Sec	Method 4046 ASTM D 257
Surface Resistivity	10 <sup>11</sup>	ohm/sq	Method 4046* ASTM D 257

### Physical Properties

Compressive Deflection at (Vertical Direction) 10%	1.5	psi	ASTM D3575 TEST B
Compressive Deflection at (Vertical Direction) 25%	4.4	psi	ASTM D3575 TEST B
Compressive Deflection at (Vertical Direction) 50%	14.5	psi	ASTM D3575 TEST B
Tensile Strength (Machine Direction)	32	Ps	ASTM D638
Elongation at Break	< 100	%	ASTM D638
Tear Resistance (Machine Direction)	9.2	lb/in	ASTM 1004
Density Range	1.7	pcf	ASTM D3575 TEST C METHOD B
Thermal Conductivity at 75 ° F	0.35 - 0.45	BTU-in/ hr.ft2	ASTM D3575 TEST E METHOD B

#### Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18  
Toa Payoh Industrial Estate  
Singapore 318992

Tel : +65 63541511  
Fax : +65 63541711  
Email : sales@pro-pack.com.sg  
Website : www.pro-pack.com.sg

Regional Offices :

**Malaysia**  
Bold Pack Industries Sdn Bhd

**Indonesia**  
PT Pro-Pack Industries

**Thailand**  
Bold-Pack Materials (Thai) Co. Ltd

**Philippines**  
Pro-Pack Materials (Philippines) Inc.

**India**  
Pro-Pack Materials India Pvt Ltd

**China**  
Pro-Pack Materials (Wuxi) Co., Ltd