

Product Data

Paper, Cleanroom CR 72g

Code : 5306 Series



Physical Properties

Component	Pulp (Cellulose)	67	g/m ²	
Component	Chemicals	5	g/m ²	
Basis Weight		72 ± 3	g/m ²	KSM7013
Caliper		86 ± 5	µm	KSM7021
Moisture		5.5 ± 0.5	%	-
Ash		0.0	%	-
Smoothness	TM	40 above	sec	KSM7028
	WS	40 above		
Tensile Strength	WD	5.0 above	kg/15mm	KSM7014
	CD	2.5 above		
Surface Resistivity		1 x 10 ¹¹ ↓	Ω/square	Super Megommeter
Static Build-Up	Before-Friction	< 5	v/cm ²	-
	After-Friction	< 40		
Particle > 0.3(µm)	Normal	1.000 ↓	count/cfm	particle counter
Extractable Ions	Sulfite (SO32-)	100 ↓	µg/cm ²	IES-RP-CC004.2 section 6.2
	Sulfate (SO42-)	100 ↓		
	Chloride (Cl-)	100 ↓		
	Nitrate (NO3-)	100 ↓		
	Sodium (Na+)	100 ↓		
	Bromide (Br-)	100 ↓		
	Potassium (K+)	100 ↓		
	Ammonium (NH4+)	100 ↓		
	Lithium (Li+)	100 ↓		
	Phosphate (PO43-)	100 ↓		
	Total	1000 ↓		
Heavy Metals	Cd	N.D.	mg/kg	SGS Testing Method
	Pb	N.D.		
	Hg	N.D.		
	Cr VI	N.D.		

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia

Bold Pack Industries Sdn Bhd

Indonesia

PT Pro-Pack Industries

Thailand

Bold-Pack Materials (Thai) Co. Ltd

Philippines

Pro-Pack Materials (Philippines) Inc.

India

Pro-Pack Materials India Pvt Ltd

China

Pro-Pack Materials (Wuxi) Co., Ltd