

## Product Data

**Paper, Tyvek**

**Code: 5306 Series**

**Model: 1057D**

### Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18  
Toa Payoh Industrial Estate  
Singapore 318992

Tel : +65 63541511  
Fax : +65 63541711  
Email : sales@pro-pack.com.sg  
Website : www.pro-pack.com.sg

Regional Offices :

**Malaysia**  
Bold Pack Industries Sdn Bhd

**Indonesia**  
PT Pro-Pack Industries

**Thailand**  
Bold-Pack Materials (Thai) Co. Ltd

**Philippines**  
Pro-Pack Materials (Philippines) Inc.

**India**  
Pro-Pack Materials India Pvt Ltd

**China**  
Pro-Pack Materials (Wuxi) Co., Ltd

### Physical Properties

Basic Weight	55, 53.0 - 58.0	g/m <sup>2</sup>	DIN EN ISO 536 <sup>(2)</sup>
Thickness	160, 100 - 230	µm	DIN EN 20534 <sup>(4)</sup>
Tensile MD <sup>(3)</sup>	140, 120 -160	N/2.54cm	DIN EN ISO 1924-2 <sup>(5)</sup>
Tensile XD <sup>(3)</sup>	145, 120 - 170	N/2.54cm	DIN EN ISO 1924-2 <sup>(5)</sup>
Elongation at Break MD <sup>(3)</sup>	14-30	%	DIN EN ISO 1924-2 <sup>(5)</sup>
Elongation at Break XD <sup>(3)</sup>	15-30	%	DIN EN ISO 1924-2 <sup>(5)</sup>
Tear Elmendorf MD <sup>(3)</sup>	4.8, 3.4 - 6.2	N	DIN EN 21974
Tear Elmendorf XD <sup>(3)</sup>	5.0, 3.8 - 6.3	N	DIN EN 21974
Opacity	96.0, 94.0 - 98.0	%	ISO 2471 <sup>(7)</sup>
Delamination (MD)	1.6, 1.2 - 2.0	N/2.54cm	ASTM D2724-87 <sup>(8)</sup>
Burst Strength	830, 700 - 940	kPA	ISO 2758
Treatment <sup>(9)</sup> Corona Antistat	YES		