

## Product Data

### Bin, Stacking Conductive

Code : 6303 series



#### Physical Properties

Specific Gravity	1.0	g / cc	ASTM D-792
Melt Flow Index (130 °C / 5 kg)	2.5	g / 10 min	ASTM D-1238
Shrinkage	1.2 - 1.4	%	-

#### Mechanical Properties

Tensile Strength	30	mpa	ASTM D-638
Elongation At Break	> 100	%	ASTM D-638
Notched Impact Strength At 23 °C	500	J / m	ASTM D-256

#### Electrical Properties

Volume Resistivity	$\leq 7 \times 10^5$	Ohm-cm	ASTM D-257
Surface Resistance	$\leq 7 \times 10^5$	Ohm	ASTM D-257

#### Dimension

Size A	88 x 89 x 42	mm	-
Size B	154 x 89 x 62	mm	-

#### Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18  
Toa Payoh Industrial Estate  
Singapore 318992

Tel : +65 63541511  
Fax : +65 63541711  
Email : sales@pro-pack.com.sg  
Website : www.pro-pack.com.sg

Regional Offices :

**Malaysia**  
Bold Pack Industries Sdn Bhd

**Indonesia**  
PT Pro-Pack Industries

**Thailand**  
Bold-Pack Materials (Thai) Co. Ltd

**Philippines**  
Pro-Pack Materials (Philippines) Inc.

**India**  
Pro-Pack Materials India Pvt Ltd

**China**  
Pro-Pack Materials (Wuxi) Co., Ltd