


Product Data

Tile, Conductive PVC Floor
StaticFlor


Model : PRO Series

Code : 7000 Series


PRO-3001




PRO-3002




PRO-3003




PRO-3004




PRO-3005




PRO-3006




PRO-3007



PRO-3008



PRO-3009



Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia

Bold Pack Industries Sdn Bhd

Indonesia

PT Pro-Pack Industries

Thailand

Bold-Pack Materials (Thai) Co. Ltd

Philippines

Pro-Pack Materials (Philippines) Inc.

India

Pro-Pack Materials India Pvt Ltd

China

Pro-Pack Materials (Wuxi) Co., Ltd

	Properties	Test Results	
Physical Features	Thickness ASTM F386	2.0mm 3.0mm	
	Size SJ/T 11236-2001	600 x 600 mm 610 x 610 mm	900 x 900 mm 914 x 914 mm
	Weight/m ² EN 430	2.0 mm : 3.24 kg/m ² 3.0mm : 4.87 kg/m ²	
	Dimension Stability EN434	0.01%	
	Flexibility ASTM F137	Dia 8mm : Pass	
	Squareness SJ/T 11236-2001	600 x 600 / 610 x 610 : ± 0.02mm	
	Residual Indentation SJ/T 11236-2001	≤ 0.15 mm	
	Abrasion Resistance ASTM D4060 (CS- 1000g, 1000 cycles)	0.0987 g	
	Hardness ASTM D2240	65 (Type D / 1 sec)	
	Static Load Limit ASTM F-970	0.02mm	


Product Data

Tile, Conductive PVC Floor
StaticFlor


Model : PRO Series

Code : 7000 Series


PRO-3001




PRO-3002




PRO-3003




PRO-3004




PRO-3005




PRO-3006




PRO-3007



PRO-3008



PRO-3009



	Properties	Test Results
Electrical Features	Electrical Resistance ANSI/ ESD S7.1 - 2005	$2.5 \times 10^4 < R < 10^6 \Omega$
	Body Voltage Generation SJ/T 11236-2001	IVI < 100 volt
	Static Decay GJB2605-1996	≤ 2 sec
Resistance To Chemical	Resistance to Chemical ASTM F925	Good (Test results available upon request)
Fire Resistance	Smoke Generated ASTM E662-6/ NFPA 258	450 or less
	Critical Radiant Flux ASTM E648-06a/ NFPA 253	Class I
	Flame Spread ASTM E 84-07/ NFPA 255	Class II
	Outgassing ASTM E 595	Excellent (Test Result available)
Miscellaneous Features	Color Fastness ISO 105 B02	≤ 6
	Water Proof Test ASTM D570	0.19%

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia

Bold Pack Industries Sdn Bhd

Indonesia

PT Pro-Pack Industries

Thailand

Bold-Pack Materials (Thai) Co. Ltd

Philippines

Pro-Pack Materials (Philippines) Inc.

India

Pro-Pack Materials India Pvt Ltd

China

Pro-Pack Materials (Wuxi) Co., Ltd