

Product Data

Sheet, Conductive PU
Foam

Code : 1105 Series



Physical Properties

Raw Material	Carbon, Polyurethane	
Density	0.082	g / cm ³
Tensile Strength	10.4	psi
Elongation	170	%
Tear	2.1	Lbs/in
Flexural Modulus	520	kgf / cm ²
Brittle Point	-75	°C
Surface Resistivity	10E3 - 10 E5	Ohm / sqmt
Thickness	0.8	Mm

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia
Bold Pack Industries Sdn Bhd

Indonesia
PT Pro-Pack Industries

Thailand
Bold-Pack Materials (Thai) Co. Ltd

Philippines
Pro-Pack Materials (Philippines) Inc.

India
Pro-Pack Materials India Pvt Ltd

China
Pro-Pack Materials (Wuxi) Co., Ltd