

## Product Data

Bag, Antistatic LDPE

Code : 1302 Series



Feature	Benefit
Permanent antistatic	ESD protection
Transparent	Identified product been pack
Non corrosive	Will not affect metal part

### Physical Properties

Tear Strength	1200	g	ASTM D922
Tensile Strength	185	Kg/sq.cm	ASTM D822
Water Absorption (24 Hr)	0.01	%	-
Heating Temperature	82 - 121	°C	-
Sealing Time	0.5 - 5	Sec	-
Maximum Temperature	93	°C	-
Minimum Temperature	15	°C	-

### Electrical Properties

Static Decay Test (from 5KV to 1% at 73°F to 15% RH)	< 2	Sec	Method 4046
Surface Resistivity	$10^{10} - 11^{11}$	Ohm / Sq.	ASTM D257

#### Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18  
Toa Payoh Industrial Estate  
Singapore 318992

Tel : +65 63541511  
Fax : +65 63541711  
Email : sales@pro-pack.com.sg  
Website : www.pro-pack.com.sg

Regional Offices :

**Malaysia**  
Bold Pack Industries Sdn Bhd

**Indonesia**  
PT Pro-Pack Industries

**Thailand**  
Bold-Pack Materials (Thai) Co. Ltd

**Philippines**  
Pro-Pack Materials (Philippines) Inc.

**India**  
Pro-Pack Materials India Pvt Ltd

**China**  
Pro-Pack Materials (Wuxi) Co., Ltd