

Product Data

**Bag, Nylon Moisture
Barrier**

Code : 1005 Series

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia
Bold Pack Industries Sdn Bhd

Indonesia
PT Pro-Pack Industries

Thailand
Bold-Pack Materials (Thai) Co. Ltd

Philippines
Pro-Pack Materials (Philippines) Inc.

India
Pro-Pack Materials India Pvt Ltd

China
Pro-Pack Materials (Wuxi) Co., Ltd

Feature	Benefit
Transparent	Identified product been packed

Physical Properties

Tensile Strength	6,000	psi	ASTM D-638
Burst Strength (Mullen)	90	psi	FTMS 191C
Tear Strength (notched)	52	gms/Mil	ASTM D-1922
Puncture Resistance	> 27	lbs	FTMS 101C
Heat Seal Strength	> 81	lbs / in width	ASTM D-1876
Elongation at break	80	%	ASTM D-822
Total Material Thickness	4	Mil	ASTM D-2103

Barrier Properties

Moisture Vapor Transmission Rate	< 0.5	gms/100 in ² / 24 hrs	MOCON
Oxygen Transmission Rate	< 0.27	gms/100 in ² / 24 hrs	ASTMD-3985(OTR)