

Product Data

**Fabric, Grid 2.5mm
Conductive (V361)**

Model : PPM - 167

Code : 3603 Series

Pro-Pack Materials Pte Ltd

Blk 970, Toa Payoh North, #04-18
Toa Payoh Industrial Estate
Singapore 318992

Tel : +65 63541511
Fax : +65 63541711
Email : sales@pro-pack.com.sg
Website : www.pro-pack.com.sg

Regional Offices :

Malaysia
Bold Pack Industries Sdn Bhd

Indonesia
PT Pro-Pack Industries

Thailand
Bold-Pack Materials (Thai) Co. Ltd

Philippines
Pro-Pack Materials (Philippines) Inc.

India
Pro-Pack Materials India Pvt Ltd

China
Pro-Pack Materials (Wuxi) Co., Ltd

Test	Warp	Weft	Unit	Method
Yarn	PFY 75D	PFY 100D	Denier	-
FCF	24 DTEX	24 DTEX	BASF	-
Density	180	97	Threads / Inch	-
Weave	0.5 TWL (2.5 mm Grid)		-	-
Width	58"/60"	58"/60"	Inch x YD	-
Weight	105	105	Gr / M ²	-
Cover Factor	2498	2498	-	-
Air Permeability	10.4	10.4	Cm ² / Cm ² / Sec	JIS-L1096
Moisture Permeability	363.3	363.3	GR / m ² / HR	JIS-L1099
Filtration Efficiency 0.3µm – 0.5µm	80 – 85	80 – 85	%	LES RP-CC-003-87-T MODIFIED
Tearing Strength	2240	2120	Gr	-
Tensile Strength	95.6	64.8	Kg	-
Friction Static Voltage	Below 10	Below 10	Volts	JIS-L1094B
Surface Resistivity	10 ⁵ - 10 ⁶	10 ⁵ - 10 ⁶	Ω/Sq	ASTM D 257
Static Decay 5,000V – 500V	0.01	0.01	Sec	FTS M4046 S101C
Abrasion Resistance	61	61	Cycles	JIS-L1096 Univ.

Laundry Recommendation

Washing	Temp: 40°C, Ph – 7.0
Rinsing	DI Water : 10e 18ω
Dry	60°C Dry Chamber with Hanger Installed
Recommendable Washing Times	≤ 50 Times

* Note: Do Not Squeeze By Hand / Do Not Iron