

Marketing Specification

PRODUCT INFORMATION


Product Description	5mm Grid ESD Fabric		
Product Model	MDF160S		
Product Code	3632-0001~3632-0019		
Recommended 1. Storage at room temperature and dry place; 2. Keep away from open flame and flammable anesthetics.			
Washing Condition	 Use detergents specifically for synthetic fibers and avoid detergents containing bleach The washing temperature is between 30-40°C and should not exceed 60°C The drying temperature should not be too high, controlled below 60°C Can be washed up to 50 times (After Wash 50 Times Surface Resistance:1.0E07≤R<1.0E09) 		

Product	3632-	3632-	3632-	3632-	3632-	3632-	3632-	3632-	3632-	3632-
Code	0001	0002	0003	0004	0005	0006	0007	0008	0009	0010
Colour Code	MDF1 60S C0	MDF1 60S C18	MDF1 60S C10	MDF16 0S C19	MDF1 60S C8	MDF16 0S C12	MDF1 60S C5	MDF1 60S C21	MDF160 S C10S	MDF- 160S-C3
Colour	White	Lake Blue	Light Gray	Ocean Blue	Dark Blue	Dark Brown	Pink	Royal Blue	Medium Grey	Light Yellow

Product	3632-	3632-	3632-	3632-	3632-	3632-	3632-	3632-	3632-
Code	0011	0012	0013	0014	0015	0016	0017	0018	0019
Colour	MDE	MDE	MDE	MDF	MDF	MDF	MDF	MDF	MDF
Colour Code	MDF 160S C6	MDF 160S C7	MDF 160S C9	160S	160S	160S	160S	160S	160S
Code	1003 C0	1603 C7	1002 C9	C12A	C16	C17	C22	C20	C23
Colour	Light Blue	Sky Blue	Apple Green	Light Brown	Olive Green	Dark Green	Red	Turquis e / Mean Green	Dark Orange- A

Rev.F, Effective Date: 14th October-2024 Page **1** of **3**

5mm Grid ESD Fabric 3632-0001~0019



PHYSICAL SPECIFICATION

No	Items	Specification	Tolerance
Α	Fabric Width	1.5m	±0.02m
В	Grid size	5 x 5mm	±0.5mm
С	Length	125m	±25m
D	Weight	110gsm	±5gsm

5mm Grid ESD Fabric 3632-0001~0019

CHARACTERISTIC

No	Items	Specification	Unit
1	Yarn	Warp: 100D Weft: 100D	Denier
2	Density	Density Warp: 160 (±2) Weft: 85 (±2)	
3	Weave	1/2 twill (5mm grid)	-
4	Heat Resistance	Up to 100°C	°C
5	Tearing Strength	Warp: 4.5 Weft: 2.9	lbf
6	Tensile Strength	Warp: 201.3 Weft: 137.7	lbf
7	Air Permeability	3.63	cm³/ s/ cm²
8	Surface Resistance	1.0E05≤R<1.0E07	Ω
9	Surface Resistance After Wash 50 Times (Clean With Mild Detergent Under 70°C)	1.0E07≤R<1.0E09	Ω

MATERIAL SPECIFICATION

Composition	
98% of Polyester Yarn & 2% of Carbon Yarn	

CUSTOMER ACKNOWLEDGEMENT

Version	Revision Date	Pro-Pack Sales PIC (Name/ Signature)	Customer Acknowledgement (Name/ Signature)
F	14 Oct. 2024		